

## Urban "easy-on" Asbestos Sealant

### Description

easy-on Asbestos Encapsulation Coating safely and completely bonds back dangerous asbestos fibres, sealing them in to prevent harm. easy-on is the only Asbestos Sealer Coating to deliver 20-year life and offer Clear, Durable, UV-stable Asbestos Protection. Once the easy-on Asbestos Encapsulation Coating is applied previously hazardous asbestos is made safe and can be washed down and cleaned if required. easy-on Asbestos Sealer is Solvent Free and Class 0 and as such suitable for both internal and external application including over previously painted asbestos surfaces.

### **Advantages**

- Clear Asbestos Encapsulation paint
- Seals in dangerous asbestos fibers
- Strong, durable and waterproof
- Tested and effective up to 20 years
- Washable and damage resistant
- Single coat Asbestos protection
- Asbestos causes 3,000 deaths PA
- Safe and cost effective alternative
- Can be used inside and outside
- UV stable and weatherproof
- Should outlast building design life
- Dependable in real world scenarios
- Proven and independently tested
- Solvent Free and Low VOC

### Simple application instructions:

Coating performance is proportional to the degree of surface preparation. Surfaces must be clean, dry (<6% moisture), undamaged and free of all contaminants prior to coating.

- 1) Add total contents of Cure tin into Resin tin and stir or re-lid and shake until mixed.
- 2) Apply one thin coat by brush, roller or spray without diluting.
- 3) If bubbles are created, flow these out with a dry brush for an optimum flat finish.
- 4) Leave to dry for 4 hours @20C and protect from dust, dirt, rain, etc.

On porous surfaces 2 coats may be necessary.

## Technical Data & Physical Data

**Colour:** Transparent

**Finish:** Gloss Sheen

**Mix Ratio:** 5 : 1 Resin/Cure

**Substrates:** Concrete, tile, mortar, existing coatings, metals, timber.

**Components:** 2 (resin + cure)

**Curing mechanism:** Chemical reaction between components

**Dry film thickness:** 25 - 50 microns

**Number of coats:** 1 (usually)

**Moisture permeability:** 35gm/ m<sup>2</sup>/24 hours

**SG of mixed product:** 1.10 kg/L

**VOC content:** <8% weight

**Calculated coverage:** 33 m<sup>2</sup> per litre @ 25 microns

**Practical coverage:** 9-33 m<sup>2</sup> per litre dependent upon surface, porosity and texture.

**Application:** By brush, roller, low pressure HVLP or conventional spray equipment.